

RTV 664, RTV 668

RTV 600 SERIES ADDITION CURE MOULDMAKING COMPOUNDS

Product Description

RTV600 series is comprised of RTV664 and RTV668. Each is a two part, addition (platinum) curing mould making product offering high durometer for applications requiring greater dimensional stability. RTV664 is a high durometer (62 Shore A). It offers excellent chemical and abrasion resistance and was designed for high production on manufacturing lines.

RTV664 may be used in food contact applications.

RTV668 is a high durometer (62 Shore A) product formulated for sulphur resistance. It is ideal for casting with masters made of pine, oak, and elm.

Key Performance Properties

- Excellent dimensional stability
- High tear strength
- High durometers 62 Shore A
- Virtually no shrinkage (room temperature cure)

Typical Product Data

Product Base	RTV 664 A	RTV 668 A
Colour	Beige	Beige
Viscosity, mPa.s	153,000	151,000
Density, g/cm ³	1.28	1.28
Catalyst	RTV 664 B	RTV 668 B
Colour	blue	green
Viscosity, mPa.s	6,000	3,800
Density, g/cm ³	1.05	1.05
Mix Ratio, (by weight)	10:1	10:1
Catalyzed Properties		
Viscosity, mPa.s	120,000	120,000
Worklife, hrs.	2	2
Demould time, hrs.	18	24
Shore A, 36 hrs.	62	62
Tensile strength, Mpa	6.4	7.2

Elongation, %	245	240
Tear Strength, N/mm	22	18
Service Temperature, °C	-60/200	-60/200
Linear Shrinkage, %	< 0.2	< 0.2

Specifications Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV1 and RTV2.

Instructions for Use

Mixing

Select a mixing container 4-5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out the RTV silicone rubber base compound and add the appropriate amount of curing agent. With clean tools, thoroughly mix the RTV base compound and the curing agent, scraping the sides and bottom of the container carefully to produce a homogeneous mixture. When using power mixers, avoid excessive speeds which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

Deaeration

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of 10 - 20 mbar. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases.

Automatic equipment designed to meter, mix, deaerate, and dispense two-component RTV silicone rubber compounds will add convenience to continuous or large volume operations.

Curing

RTV664 and RTV668 silicone rubber compounds will cure sufficiently in 24 hours at 25C. To achieve faster cure speeds, elevated temperatures may be used.

Handling and Safety

Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.

Storage and Warranty Period

The warranted shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers below 27° C.

Availability

RTV664 and RTV668 are available in kits of 450g, 5kg, 20 kg and 225 kg.



MOMENTIVE
performance materials

RTV 664, RTV 668

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Momentive and M-design logo are trademarks of Momentive Performance Materials Inc.
Copyright 2008 Momentive Performance Materials, Inc. All rights reserved.
12/8/08 - EU-50-101-00