

SS PU21445

A halogen free, flame retardant, semi-rigid potting resin used in light to medium voltage electrical applications

Application	Key Properties
<ul style="list-style-type: none"> Encapsulation of transformers Cable joints Wide range of substrates Low to medium voltage electrical and electronic applications 	<ul style="list-style-type: none"> Room temperature cure Low cure exotherm High impact resistance Non-toxic Good electrical insulation characteristics

Description	
<ul style="list-style-type: none"> Basic Resin Hardener 	Two-component polyurethane system SS PU21445/A SS PU21445/B

Physical Data (approx. – values)	SS PU21445/ A	SS PU21445/ B	SS PU21445
Colour	Black Grey	Brown Brown	Black Grey
Specific Gravity	1.72	1.24	1.65
Viscosity (mPas) @ 25°C	14000	4900	6000

Cure Schedule (150ml)	Working Life	Gel Time	Light Handling	Full Cure
Temperature	(minutes)	(minutes)	(hours)	(hours)
RT*	15	45	24	168
60°C	-	-	4	4
80°C	-	-	2	2

* RT is defined as 20-25°C

The above are typical values and will vary depending on the cured mass and application. Hotter temperatures may be used for faster cure but will result in higher post cure shrinkage and higher cure exotherm. Experimentation and testing is suggested to avoid side effects. For maximum properties a post cure may be required – Contact our technical service department for advice.

Processing

Mix ratio by weight 8.4:1
 Mix ratio by volume 6.1:1

Typical Properties	Result	Unit
Water absorption (30 days @25°C)	0.6	%
Flammability	Flame retardant	
Hardness	~ 50	Shore D
Heat Deflection Temperature	Flexible	
Operating Temperature	-40 - +125	°C (application & geometry dependent)
Thermal Conductivity	0.75	W/mK
Tensile Strength	5.3	mPa
Compressive Yield Strength	< 10	mPa
Coefficient of Linear Expansion	75-100	ppm/°C
Volume Resistivity	12 ¹⁰	ohm.cm
Surface Resistivity	12 - 14 ¹⁰	ohm.cm
Peak Exotherm (150ml @ 20°C)	40	°C
Shrinkage (Volume)	0.5	%
Elongation at break	~30	%
Dielectric Strength	16	kV/mm
Permittivity (ε)	4.6	50Hz
Loss Tangent (Tanδ)	0.3	50Hz
Comparative Tracking Index	> 600	v

Approvals	
RoHS compliant	Yes
UL94 V-0	No
REACH (SVHC concentration)	Refer to SDS

Packaging

SS PU21445 is available in Bulk, Twinpacks Sets & Kits

Availability

Available through distribution

Twinpacks - Part Numbers

SS PU21445/BK/025	SS PU21445/BK/250
SS PU21445/BK/050	SS PU21445/BK/500
SS PU21445/BK/100	SS PU21445/BK/1000

Twinpacks are pre-weighed resin and hardener components contained in a tough flexible film, separated by a removable clip and rail. Once the clip and rail is removed the resin and hardener is thoroughly mixed within the bag and is immediately ready for use. Mixing will normally take ~ 2 minutes due to the viscosity; but pay special attention to the corners. Twinpacks are ideal for small to medium production runs, prototyping and on-site or field use. The twinpack weight/volume may also be tailored to a specific size on request.

Bulk Materials - Part Numbers

SS PU21445/BK/1KG	SS PU21445/NC/1KG
SS PU21445/BK/5KG	SS PU21445/NC/5KG
SS PU21445/BK/10KG	SS PU21445/NC/10KG
SS PU21445/BK/25KG	SS PU21445/NC/25KG
SS PU21445/NC/25KG	SS PU21445/NC/250KG
SS PU21445/BK/250KG	SS PU21445/NC/IBC
SS PU21445/BK/IBC	

Both resin and hardener are supplied in 5kg, 25kg and 200ltr drums and fully evacuated and ready for use.

Care should be taken to ensure when mixing the resins air is not entrained in the mixture. If this is unavoidable the mixed resin and hardener should be re-evacuated before dispensing. The bulk resin and hardener materials can be dispensed from suitable dispensing machinery, details provided by Fluid Research on request.

Kits and Sets Part Numbers

SS PU21445/BK/1.9KGKIT	SS PU21445/BK/4.5KGSET
SS PU21445/BK/5KGKIT	SS PU21445/BK/11.5KGSET
SS PU21445/BK/8.25KGKIT	
SS PU21445/BK/25KGKIT	

Kits and Sets are provided in separate containers to the correct ratio.

In Kit form, pour the small container into the larger container and use it as a mixing vessel.

Stir well using an appropriate mixer until homogeneous.

Note: Incomplete mixing will be characterised by erratic or partially incomplete cure even after extended time periods.

Cleaning

All equipment contaminated with mixed material should be cleaned before the material has hardened. TS130 is a suitable non-flammable cleaning agent, although other solvents may be found suitable. TS130 will also remove cured material provided it can soak for several hours.

Storage and Shelf Life

Material stored in the original unopened containers under cool dry condition between 15° and 25°C will have a shelf life of at least two years. Once used the containers must be kept sealed to prevent effects from water, air or contaminants.

Health and Safety

Polyurethane resin systems may cause sensitisation by skin contact or inhalation may be corrosive, harmful or toxic. It is therefore strongly recommended that skin and eye contact is avoided by the using of appropriate personal protective equipment such as gloves, safety glasses or goggles and overalls. Wash any contamination from the skin immediately and thoroughly and do not eat, smoke or drink in the working vicinity.

Under normal working conditions a good source of ventilation is adequate, however if the material is heated, or where vapour levels are likely to exceed the occupational exposure limits appropriate respiratory protection must be worn. Local exhaust ventilation (LEV) may be required especially for curing ovens or where large volumes of material are curing. The above is given as a guide only; please refer to RL/SS PU21445 Health and Safety data or our Technical Service Department for individual/specific advice.

Contact Details

Silicone Solutions Limited
Unit H2, Europe Way
Stoneclough Road
Radcliffe
Manchester
M26 1GG

Tel: 01204 863290
Fax: 01204 863299
Email: sales@silicone-solutions.co.uk
Web: www.silicone-solutions.co.uk